


Technical Data Sheet Doorstrip

	Standard	Method
Density	1.22	DIN53479 +/-2
Shore A	76	DIN53505 +/-3
Brittle Point	-35	DIN53372 C
Max Op. T	+45	DIN53372 C
Tensile Str.	18	DIN53455
Stress Test	320	DIN53455 %
Flammable	None	All Inflammable
Noise test	28db	DIN52210 decibel
Flexibility	-37	DIN51949 break
UV Test	248	Days no change



All compounds are tested and certified by the FDA Food and Drug administration for food contact usage. All compounds are manufactured to a number of medical specifications for usage in a medical, food and laboratory environment. All our PVC-Doorstrips are manufactured in the EU.